

WORSTED YARN FOR PIECE DYEING

Patent number: JP5214626
Publication date: 1993-08-24
Inventor: KAIMORI MICHINOBU; SAKURAI TADAATSU;
YOSHIDA TATSUYA; OHASHI SHIGEHIO
Applicant: KANEBO LTD
Classification:
- international: D02G3/04; D06M11/07; D06M13/00; D06M101/12
- european:
Application number: JP19920048012 19920203
Priority number(s): JP19920048012 19920203

Report a data error here

Abstract of JP5214626

PURPOSE:To obtain worsted yarn for piece dyeing capable of simply producing melange yarn good in mixing degree of color and having various kinds of colors. **CONSTITUTION:**The objective worsted yarn for piece dyeing is constituted by using at least partially printed print wool fiber and a modified wool fiber to which chlorination or chlorination and resin finishing are applied.

Data supplied from the **esp@cenet** database - Worldwide

JP 5-214626 discloses a method for improving stain resistance of a cloth by applying a solution containing a stain blocker. Tannic acid and a sulphonated phenol-or naphthol-aldehyde condensation is exemplified as the stain blocker in the eight publications. A combination of the two compositions is not described.

(19)日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11)特許出願公開番号

特開平5-214626

(43)公開日 平成 5 年(1993) 8 月24日

(51)Int.Cl.⁵

識別記号

庁内整理番号

F I

技術表示箇所

D 0 2 G 3/04

D 0 6 M 11/07

13/00

// D 0 6 M 101:12

7199-3B

D 0 6 M 3/ 00

審査請求 未請求 請求項の数 2 (全 6 頁)

(21)出願番号 特願平4-48012

(22)出願日 平成 4 年(1992) 2 月 3 日

(71)出願人 000000952

鐘紡株式会社

東京都墨田区墨田五丁目17番 4 号

(72)発明者 改森 道信

奈良市帝塚山南一丁目 7 番19号

(72)発明者 櫻井 忠温

四日市市波木が丘町 8 - 3 番地

(72)発明者 吉田 達也

大阪市城東区鳴野西 5 - 12 - 6 - 407

(72)発明者 大橋 茂浩

大阪府高槻市清水台一丁目18番12号

(74)代理人 弁理士 松川 克明

(54)【発明の名称】 後染用梳毛糸

(57)【要約】

【目的】 後染めすることによって、色の混ざり具合が良好でこなれの良い様々な色彩の霜降糸を簡単に製造できる後染用梳毛糸を提供する。

【構成】 後染用梳毛糸を、少なくとも部分的に捺染されたプリント羊毛繊維と、塩素化処理または塩素化・樹脂加工処理が施された改質羊毛繊維とを用いて構成するようにした。